Application No.: 10/659888 Docket No.: AD6937USNA

Page 2

Amendments to Specification

On page 8 of the specification, line 25 to the end of the page, Table 1, Example 4 is amended as follows:

Table 1

Example	Wt.	MATRIX	Wt.	RUBBER	WŁ.	Mineral	Filler/	Sample	Standard
No.	%		%		%	Filler	Rubber	Average	Deviation
							Ratio	IZOD	Izod
	i		{		1			Ft-lb/in	Ft-lb/in (J/m)
						l		(J/m)	
Control	90	В	10	¢	0		0	9.5 (507)	0.4 (19)
1									
2	85	В	10	С	5	Α _	0.5	9.1 (486)	0.5 (27)
3	80	В	10	С	10	Α	1.0	10.4 (555)	0.7 (39)
				l	L				
4	85	В	10	С	15	Α	1.5	4.5 (240)	2.7 (143)
	75								